

American Black Walnut



Please contact one of our helpful experts for more information **+44(0) 1373 469905**

American Black Walnut (steamed) timber is usually stocked in square edge 4" and wider, generally 4" - 7" boards on average within a standard FAS IF graded pack. Favoured because it is easy to work and gives a very attractive 'quality' appearance. Black walnut will have some knots, and sapwood. Kiln dried stocks of 26mm, 32mm, 38mm, 51mm, 63mm and 76mm with lengths generally 2m - 3m.

Latin name Juglans nigra

Also known as American walnut, black walnut

Environmental Not listed in CITES. Available from well-managed sources.

Distribution Black walnut is widely distributed throughout North America from south Ontario southward to Texas, and in the east from Maine to Florida, but it is not plentiful, firstly because its growth is scattered, and secondly, because of the clearing of ground for cultivation and the demands for the timber have exhausted the supply in many areas.

American Black Walnut Properties

The Tree Under favourable conditions, the tree attains a height of 30m and a diameter of 1.5m or more, the bole often being clear for 15m to 18m.



American Black Walnut



Please contact one of our helpful experts for more information **+44(0) 1373 469905**

The Timber The sapwood is usually narrow, and pale brown in colour, the heartwood varying in colour from rich chocolate-brown to purplish-black. The wood has a fine even texture and a rather coarse grain, and weighs about 660 kg/m³ when dried.

Drying Dries rather slowly with possible honeycombing.

Working Qualities Good - the timber is moderately hard, tough, strong and is easily worked. It finishes well and takes an excellent polish. Good for nailing, screwing and gluing. Good stability.

Physical Properties Hard timber with medium density. Moderate bending and crushing properties. Low stiffness. Good steam bending properties.

Durability Moderately durable. Resistant to heartwood decay. Sapwood liable to attack by powder post beetle.

Treatability Extremely difficult

Moisture Movement Medium

Density (mean, Kg/m³) 660

Texture Coarse

Availability Limited availability

Working with American Black Walnut

Use(s) Furniture, light construction, cabinet making, architectural interiors, high class joinery, doors, flooring, paneling.



American Black Walnut



Please contact one of our helpful experts for more information **+44(0) 1373 469905**

Colour(s) Dark brown/ black (rich dark brown) with almost white pale sapwood.

What is FAS Grade

The FAS grade, which derives from an original grade "First and Seconds", will provide the user with long, clear cuttings - best suited for high quality furniture, interior joinery and solid wood mouldings. Minimum board size is 6" (152mm) and wider and 8' (2.44m) and longer. The FAS grade includes a range of boards that yield from 83.3% (10/12ths) to 100% clear-wood cuttings over the entire surface of the board. The clear cuttings must be a minimum size of 3" (76mm) wide by 7' (2.13m) long or 4" (102mm) wide by 5' (1.52m) long. The number of these cuttings permitted depends on the size of the board with most boards permitting one to two. The minimum width and length will vary, depending on species and whether the board is green or kiln dried. Both faces of the board must meet the minimum requirement for FAS.

Timbersource are a leading online timber merchant in the UK, supplying American Black Walnut timber to the joinery, carpentry, construction, retail and building trade at competitive prices.

